

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-333159

(43)Date of publication of application : 17.12.1996

(51)Int.Cl. C04B 35/49

H03H 3/02

(21)Application number : 07-136487 (71)Applicant : MATSUSHITA
ELECTRIC IND CO
LTD

(22)Date of filing : 02.06.1995 (72)Inventor : FUJINAKA YUJI

(54) PIEZOELECTRIC CERAMIC COMPOSITION AND PRODUCTION OF PIEZOELECTRIC RESONATOR USING THE SAME

(57)Abstract:

PURPOSE: To obtain a piezoelectric resonator having small variation in piezoelectricity and resonant frequency in a humidified atmosphere and excellent in thermal shock resistance.

CONSTITUTION: A silver electrode 2 is formed on a piezoelectric ceramic 1 obtained by polarizing a sintered material of a piezoelectric ceramic composition comprising a main component expressed by

$\text{Pb}(\text{Zn}_{1/3}\text{Nb}_{2/3})\text{XTiYZrZrO}_3$


($X=0.01-0.50$, $Y=0.285-0.75$,

$Z=0.125-0.680$; $X+Y+Z=1$) added with

0.1-10.0wt.% of a compound of

$\text{Pb}(\text{Me}_{1/2}\text{Te}_{1/2})\text{O}_3$ (Me is at least one kind of metal selected from the group consisting of Mn, Co, Ni and Cu),

annealing at 0.4-0.8 times of Curie temperature for ≥ 1 hr and holding at a normal temperature for ≥ 48 hr and polishing.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's
decision of rejection]

[Kind of final disposal of application
other than the examiner's decision of
rejection or application converted
registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office